

# OK 68.81



OK 68.81 is a high-alloyed electrode which deposits a ferritic-austenitic duplex weld metal with approx. 40% ferrite. It is resistant to stress corrosion and is highly insensitive to dilution. Good scaling resistance up to 1150°C. OK 68.81 is used for joining dissimilar steels, steels with reduced weldability and buffer layers prior to hardfacing. Applications: rolls, forging dies, hot-work tools, dies for plastics and so on.

<b>Classifications</b>	SFA/AWS A5.4 : E312-17 EN 14700 : E Fe11 EN ISO 3581-A : E 29 9 R 3 2 Werkstoffnummer : 1.4337
<b>Approvals</b>	CE EN 13479 Seproz UNA 272580

Approvals are based on factory location. Please contact ESAB for more information.

<b>Welding Current</b>	DC+, AC
<b>Ferrite Content</b>	FN 30 - 50
<b>Alloy Type</b>	Stainless duplex
<b>Coating Type</b>	Acid Rutile

## Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>AWS</b>			
As Welded	610 MPa	790 MPa	25 %

## Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>AWS</b>		
As Welded	20 °C	30 J

## Typical Weld Metal Analysis %

C	Mn	Si	Ni	Cr	Mo	N	Ferrite FN
0.13	0.9	0.7	10.2	28.9	0.04	0.09	40

## Deposition Data

Diameter	Current	Voltage	Number of electrodes/ kg weld metal	Fusion time per electrode at 90% I max	Deposition Efficiency %	Deposition Rate @ 90% I max
2.0 x 300.0 mm	40-60 A	22 V	123	41 sec	64 %	0.7 kg/h
2.5 x 300.0 mm	50-85 A	24 V	78	48 sec	64 %	0.9 kg/h
3.2 x 350.0 mm	60-125 A	25 V	42	65 sec	62 %	1.3 kg/h
4.0 x 350.0 mm	80-175 A	26 V	26	66 sec	62 %	2.0 kg/h
5.0 x 350.0 mm	150-240 A	28 V	17	68 sec	65 %	3.2 kg/h